

**PRODUCT INFORMATION**
**sawaloom® 6389**

**Type of Nonwoven** Nonwoven, thermally and mechanically bonded, without chemical binders. Progressive construction. Clean air side thermally smoothed.

**Fiber Composition** 100 % Polyester

**Recommendation for Application** ISO 16890 ISO Coarse

**Recommendation for Application** EN 779:2012 M5

Property	Method	Average
----------	--------	---------

<b>Basis Weight</b>	NWSP 130.1	150 g/m <sup>2</sup>
---------------------	------------	----------------------


<b>Thickness (0,05 N/cm<sup>2</sup>)</b>	NWSP 120.6	6 mm
--	------------	------

<b>Flammability</b>	DIN 53438	F1/F1/K1
---------------------	-----------	----------

This information is provided in good faith but Sandler cannot guarantee its accuracy or completeness. The end user is advised to evaluate the product and use it only in compliance with all applicable laws and regulations. This is not a specification. Properties are given as typical values.

Thickness measured under relaxed conditions. May vary after packaging, storage and transport.

SA 192



Druckverlaufskurve = Mittelwert aus mehreren Einzelwerten